



SRPNP
FOR YOUR BENEFITS FOR OUR WIN-WIN

NINGBO SURE PAPER CO.,LTD.



NINGBO SURE PAPER CO.,LTD

Room 801-802, Building B, Hongtai Di Biao

55 Haiyan North Road, Yinzhou, Ningbo

Website: <https://www.sure-paper.com>

双面涂布铜版卡 Art-board Standard										
检测项目 Items	单位 Unit	检验方法 Test Method	偏差 Tolerance	标准 Standard						
定量 Grammage	g/m ²	GB/T451.2 ISO536	±3%	210	230	250	300	350	400	
厚度 Thickness	μm	GB/T451.3 ISO534	±15	230	255	285	350	410	440	
泰伯挺度 Taber Stiffness	CD	mN·m	GB/T22364 ISO2493	目标值 Target	2.30	2.60	3.00	5.40	7.90	9.90
				最小值 Min	2.00	2.40	2.60	4.60	6.70	8.40
	MD			目标值 Target	4.10	4.70	5.80	10.2	14.7	19.8
				最小值 Min	3.60	4.00	4.90	8.70	12.5	16.8
Cobb(60s)	Top	g/m ²	GB/T1540 ISO535	≤	60					
	Back			≤	60					
PPS 表面粗糙度 Surface Roughness	μm	GB/T22363 ISO8791	≤	1.6						
印刷表面强度 IGT-Picking-Top/Back	m/s	GB/T22365 ISO3783	≥	1.5						
层间结合强度 Ply Bond	J/m ²	GB/T26203 TAPPI 569	≥	130						
亮度 Top/Back Brightness (D65)	%	GB/T7974 ISO2470	≥	89						
光泽度 75 ° Gloss-Top/Back	%	GB/T8941 ISO8254	≥	55						
水分 Moisture	%	GB/T462 ISO287	±1.5	7.0						
偏斜度-平张 Squareness	mm	GB/T451.1	-	0~2						
尺寸偏差 Size Deviation	mm		-	0~2						
检测条件 Testing Condition: 温度 Temperature: (23±1) °C 相对湿度 Relative Humidity: (50±2) %										

Features

Good smoothness, good interlayer bonding strength, excellent flatness

Good uniformity, good printing reduction

Uniform ink absorption and good surface glossiness, low ink consumption, high printing saturation

FSC/PEFC certified, compliant with ROHS/REACH/FDA and other directives and regulations

Applications

Clothing tags

Advertising DM inserts

Desktop calendars

Promotional brochures

Literacy cards

Boarding passes