



NINGBO SURE PAPER CO.,LTD.



NINGBO SURE PAPER CO.,LTD

Room 801-802, Building B, Hongtai Di Biao,55 Haiyan North Road, Yinzhou, Ningbo
 Website: <https://www.sure-paper.com>

C2S Art Paper Gloss Grade

项目 Item	单位 Unit	测试方法 Measurement	Technical Data(A)							
			80 GSM	90 GSM	100 GSM	105 GSM	115 GSM	120 GSM	128 GSM	130 GSM
基重 Basis Weight	g/m ²	IS0536	80±3	90±3	100±4	105±4	115±4	120±4	128±4	130±4
厚度 Thickness	μm	IS0534	65±4	72±4	80±4	84±4	92±4	96±4	102±4	104±4
白度 Brightness	%	ISO2470-1	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2
不透明度 Opacity	%	ISO2471	≥89	≥90	≥92	≥92	≥93	≥94	≥95	≥95
光泽度 Gloss	μm	ISO8791-4	65±5	65±5	65±5	65±5	65±5	65±5	65±5	65±5
粗糙度 Roughness	%	T480	≤1.6	≤1.6	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4

项目 Item	单位 Unit	测试方法 Measurement	Technical Data(B)													
			140 GSM	150 GSM	157 GSM	170 GSM	180 GSM	190 GSM	200 GSM	210 GSM	230 GSM	250 GSM	260 GSM	300 GSM	350 GSM	
基重 Basis Weight	g/m ²	IS0536	140±5	150±5	157±6	170±6	180±6	190±7	200±8	210±8	230±9	250±9	260±9	300±10	350±10	
厚度 Thickness	μm	IS0534	120±4	129±4	134±4	146±5	154±5	164±5	174±5	183±6	201±6	225±7	234±7	270±8	330±8	
白度 Brightness	%	ISO2470-1	89±2													
不透明度 Opacity	%	ISO2471	98.0±1.5			98.5±1.5										
光泽度 Gloss	%	T480	67±5									65±5				
粗糙度 Roughness	μm	ISO8791-4	≤1.4											≤1.6		