

Paper Technical Data Sheet

RELEASE PAPER

Items	Unit	Standards	Standards	Standards	Standards	Standards
		30	35	38	40	48
定量 Grammage	g/m ²	30.0±1.5	35.0±1.5	38.0±1.5	40.0±1.5	48.0±1.5
厚度 Caliper	μm	40	43	46	48	50
BEKK 平滑度 Smoothness	s	Front ≥80.0 Back ≥15.0	Front ≥80.0 Back ≥15.0	Front ≥80.0 Back ≥15.0	Front ≥80.0 Back ≥15.0	Front ≥80.0 Back ≥15.0
亮度-Top/Back Brightness(D65)	%	≥83.0	≥83.0	≥83.0	≥83.0	≥83.0
撕裂强度 Tear strength	kN/m MD kN/m CD	180 190	180 200	200 220	220 240	230 250
耐折度 CD Folding	Times	≥19	≥20	≥20	≥20	≥20
抗张指数 MD Tensile index	N.m/g	≥48.0	≥49.0	≥49.0	≥50.0	≥50.0
吸水值 Water Absorptiveness	g/m ²	Front ≥23.0 Back ≥25.0	Front ≥23.0 Back ≥25.0	Front ≥24.0 Back ≥26.0	Front ≥24.0 Back ≥26.0	Front ≥25.0 Back ≥27.0
水分 Moisture	%	5.0±1.0	5.0±1.0	5.0±1.0	5.0±1.0	5.0±1.0

Feature:

- 100% virgin pulp, resistance, strong inherent strength.
- ISO 9001:2000, SGS, FSC are ALL AVAILABLE.
- Recyclable and biodegradable.

Usage:

Release paper is uncoated paper, can be used as base paper of Silicone Paper.