

**SRPNP**

FOR YOUR BENEFITS FOR OUR WIN-WIN

NINGBO SURE PAPER CO.,LTD.

FSC

COC-321559

NINGBO SURE PAPER CO.,LTD

Room 801-802, Building B, Hongtai Di Biao, 55 Haiyan
North Road, Yinzhou , NingboWebsite: <https://www.sure-paper.com>

High White Woodfree Paper/Bond Paper

Product Features:

- All wood pulp paper, which selected high-quality wood pulp
- Good formation, high thickness and stiffness
- High strength, good dimensional stability and accurate multi-color overprint; suitable for high-speed rotary offset (4colors) and sheet fed offset printing
- High brightness, bright color, good dot reproducibility, suitable for refined books, magazines and other requirements

| 检测项目 Items | 单位 Unit | 检验方法 Test Method | 标准 Standard | | | | | | | | | |
|------------------------------------|------------------|-----------------------|------------------------|----------|----------|----------|-----------|-----------|-----------|-----------|-----------|-----------|
| | | | 60 | 65 | 70 | 75 | 80 | 90 | 95 | 100 | 115 | 120 |
| 定量 Grammage | g/m ² | GB/T451.2 ISO536 | 60 ±2 | 65 ±2 | 70 ±2 | 75 ±2 | 80 ±2 | 90 ±2 | 95 ±2 | 100 ±3 | 115 ±3 | 120 ±3 |
| 厚度 Thickness | µm | GB/T451.3 ISO534 | 76 ±4 | 81 ±4 | 88 ±4 | 94 ±4 | 100 ±4 | 108 ±4 | 115 ±4 | 120 ±4 | 135 ±4 | 142 ±4 |
| Cobb-Top/Back (60s) | g/m ² | GB/T1540 ISO535 | 20.0-45.0 | | | | | | | | | |
| 亮度-Top/Back Brightness (D65) | % | GB/T7974 ISO2470 | 100.0±3.0 | | | | | | | | | |
| 视白度 CIE Whiteness | % | GB/T22880 ISO11475 | 148.0±3.0 | | | | | | | | | |
| 不透明度 Opacity | % | GB/T1543 ISO2471 | ≥86.0 | | ≥90.0 | | | | ≥93.0 | | | |
| BEKK 平滑度 Smoothness | s | GB/T456 ISO5627 | Top: ≥40.0 Back: ≥35.0 | | | | | | | | | |
| 水分 Moisture | % | GB/T462 ISO287 | 5.5±1.0 | | | | | | | | | |
| 耐折度 CD Folding | Times | GB/T457 ISO5626 | ≥5 | | | | | | | | | |
| 印刷表面强度 IGT-Picking | m/s | GB/T22365 ISO3783 | ≥1.8 | | | | | | | | | |
| 抗张指数 MD Tensile index | N.m/g | GB/T12914 ISO1924 | ≥55.0 | | | | | | | | | |