

# NINGBO SURE PAPER CO.,LTD

## Specifications

**Bible Paper**

**Jun., 2024 C Edition**

<b>Item</b>	<b>Unit</b>	<b>Test Method Reference</b>	<b>50 g/m<sup>2</sup></b>	<b>55 g/m<sup>2</sup></b>	<b>60g/m<sup>2</sup></b>	<b>70 g/m<sup>2</sup></b>	<b>80 g/m<sup>2</sup></b>	<b>120 g/m<sup>2</sup></b>
<b>Basis Weight</b>	<b>g/m<sup>2</sup></b>	ISO 536	<b>50±4</b>	<b>55±4</b>	<b>60±4</b>	<b>70±4</b>	<b>80±4</b>	<b>120±5</b>
<b>Thickness</b>	<b>μm</b>	T 411	<b>61±5</b>	<b>67±5</b>	<b>72±5</b>	<b>83±5</b>	<b>95±5</b>	<b>143±5</b>
<b>Brightness</b>	<b>%</b>	ISO 2470-1	<b>64±3</b>	<b>64±3</b>	<b>64±3</b>	<b>64±3</b>	<b>64±3</b>	<b>64±3</b>
<b>Opacity</b>	<b>%</b>	ISO 2471	<b>≥83</b>	<b>≥84</b>	<b>≥85</b>	<b>≥87</b>	<b>≥89</b>	<b>≥92</b>
<b>Smoothness (Bekk)</b>	<b>s</b>	ISO 5627	<b>90±20</b>	<b>90±20</b>	<b>80±20</b>	<b>60±20</b>	<b>60±20</b>	<b>50±20</b>