

TECHINICAL SPECIFICATION

技术指标

Specification 产品		38gsm silicone coated baking paper 38gsm双面涂硅烘焙纸		
PARAMETERS 指标	UNIT 单位	Reference 范围	Testing Standard 检测标准	Testing Result 检测结果
Grammage 克重	g/sqm	Tolerance: ±2g	ISO536: 2012(E)	38.3g/m ²
Thickness 厚度	µm	40-50	ISO534:2011(E)	40µm
Size 尺寸	mm	±2mm	GB/T 451.1	380mm
Tear Strength 撕裂度				
MD纵向	mN	≥90	ISO 1974:2012(E)	114
CD横向	mN	≥100	ISO 1974:2012(E)	125
Tensile Strength 抗张强度				
MD纵向	KN/m	≥2.8	ISO 1924-2:2008(E)	3.5
CD横向	KN/m	≥1.4	ISO 1924-2:2008(E)	1.6
Water Absorptiveness (Cobb 60S) 吸水值	g/m ²	11~26	ISO 535:2014(E)	19.8
Breaking length 干断裂长				
MD纵向	Km	≥7.0	GB/T 12914-2008	7.14
CD横向	Km	≥3.98	GB/T 12914-2008	4.37
测试条件: 加热200℃, 20分钟 Testing Condition: After heating (200℃, 20minutes)				
Tear Strength 撕裂度				
MD纵向	mN	≥60	ISO 1974:2012(E)	104
CD横向	mN	≥60	ISO 1974:2012(E)	87
Heat Resistance 耐高温性	℃	≥230	Baking in the oven for 20 minutes	PASS
Dirt Count 尘埃度				
<2.0mm ²	个/m ² pcs/m ²	≤100	GB/T 1541	PASS
2.0mm ² ~3.0mm ²		≤10	GB/T 1541	PASS
>3.0mm ²		0	GB/T 1541	PASS
Odour 气味	等级	≤1级	EN1230 Part1	PASS
Fluorescent substance 荧光性物质				
wavelength 254nm	/	Negative	GB31604.47-2016	Negative
wavelength 365nm	/	Negative	GB31604.47-2016	Negative

TECHINICAL SPECIFICATION

技术指标

Specification 产品		39gsm silicone coated baking paper 39gsm双面涂硅烘焙纸		
PARAMETERS 指标	UNIT 单位	Reference 范围	Testing Standard 检测标准	Testing Result 检测结果
Grammage 克重	g/sqm	Tolerance: ±2g	ISO536: 2012(E)	39.2g/m ²
Thickness 厚度	µm	40-50	ISO534:2011(E)	42µm
Size 尺寸	mm	±2mm	GB/T 451.1	380mm
Tear Strength 撕裂度				
MD纵向	mN	≥90	ISO 1974:2012(E)	115
CD横向	mN	≥100	ISO 1974:2012(E)	126
Tensile Strength 抗张强度				
MD纵向	KN/m	≥2.8	ISO 1924-2:2008(E)	3.6
CD横向	KN/m	≥1.4	ISO 1924-2:2008(E)	1.7
Water Absorptiveness (Cobb 60S) 吸水值	g/m ²	11~26	ISO 535:2014(E)	19.8
Breaking length 干断裂长				
MD纵向	Km	≥7.0	GB/T 12914-2008	7.15
CD横向	Km	≥3.98	GB/T 12914-2008	4.38
测试条件: 加热200℃, 20分钟 Testing Condition: After heating (200℃, 20minutes)				
Tear Strength 撕裂度				
MD纵向	mN	≥60	ISO 1974:2012(E)	105
CD横向	mN	≥60	ISO 1974:2012(E)	89
Heat Resistance 耐高温性	℃	≥230	Baking in the oven for 20 minutes	PASS
Dirt Count 尘埃度				
<2.0mm ²	个/m ² pcs/m ²	≤100	GB/T 1541	PASS
2.0mm ² ~3.0mm ²		≤10	GB/T 1541	PASS
>3.0mm ²		0	GB/T 1541	PASS
Odour 气味	等级	≤1级	EN1230 Part1	PASS
Fluorescent substance 荧光性物质				
wavelength 254nm	/	Negative	GB31604.47-2016	Negative
wavelength 365nm	/	Negative	GB31604.47-2016	Negative

TECHINICAL SPECIFICATION

技术指标

Specification 产品		40gsm silicone coated baking paper 40gsm双面涂硅烘焙纸		
PARAMETERS 指标	UNIT 单位	Reference 范围	Testing Standard 检测标准	Testing Result 检测结果
Grammage 克重	g/sqm	Tolerance: ±2g	ISO536: 2012(E)	40.2g/m ²
Thickness 厚度	µm	40-50	ISO534:2011(E)	44µm
Size 尺寸	mm	±2mm	GB/T 451.1	380mm
Tear Strength 撕裂度				
MD纵向	mN	≥90	ISO 1974:2012(E)	116
CD横向	mN	≥100	ISO 1974:2012(E)	127
Tensile Strength 抗张强度				
MD纵向	KN/m	≥2.8	ISO 1924-2:2008(E)	3.7
CD横向	KN/m	≥1.4	ISO 1924-2:2008(E)	1.8
Water Absorptiveness (Cobb 60S) 吸水值	g/m ²	11~26	ISO 535:2014(E)	19.8
Breaking length 干断裂长				
MD纵向	Km	≥7.0	GB/T 12914-2008	7.17
CD横向	Km	≥3.98	GB/T 12914-2008	4.39
Tear Strength 撕裂度				
测试条件: 加热200℃, 20分钟 Testing Condition: After heating (200℃, 20minutes)				
MD纵向	mN	≥60	ISO 1974:2012(E)	107
CD横向	mN	≥60	ISO 1974:2012(E)	91
Heat Resistance 耐高温性	℃	≥230	Baking in the oven for 20 minutes	PASS
Dirt Count 尘埃度				
<2.0mm ²	个/m ² pcs/m ²	≤100	GB/T 1541	PASS
2.0mm ² ~3.0mm ²		≤10	GB/T 1541	PASS
>3.0mm ²		0	GB/T 1541	PASS
Odour 气味	等级	≤1级	EN1230 Part1	PASS
Fluorescent substance 荧光性物质				
wavelength 254nm	/	Negative	GB31604.47-2016	Negative
wavelength 365nm	/	Negative	GB31604.47-2016	Negative